

CORD

RIBBON

BRAID

PIPING

KNIT TAPE

STRETCH

ORGANIC

**FUNCTIONALITY**

WRAPPING

MOTIF

PROCESSING

# DEO - SMILE


デオ スマイル

コットン消臭スピン

Quality Samples

Cotton	100%
ROLL 100m	
先染 Yarn Dyeing	

No.1900



●試験結果 消臭綿スピン M C/# 半晒 Cotton 100% [(社)繊維評価技術協議会にて]

臭気成分	初発濃度 (ppm)	減少率 (基準値)	DEO - SMILE (半晒) [2時間後]	洗濯10回後
アンモニア	100	70%以上	99%以上 [10分後 83%]	99%
酢酸	50	80%以上	95%以上	97%
イソ吉草酸	約38	85%以上	97%以上	99%

※洗濯収縮率《-7.3%》



(商標登録第5388459号)



このタグは品番No1901にて在庫しております。

FUNCTIONALITY

■瞬時に消臭。汗も尿もサッと消臭。

汗や尿(アンモニア)などの液体の悪臭は瞬時に消臭します。

■洗えば消臭力が回復。だから効果が長続き。

何回洗濯しても効果が復元し、消臭力を持続します。

洗濯時の注意事項

- 1.中性洗剤を使用して下さい。
- 2.漂白剤を使用の際は酸素系を使用して下さい。

●臭気成分一覧

臭気成分	汗臭	加齢臭	排泄臭	タバコ臭	生ゴミ臭
アンモニア	○	○	◎尿	○	○
酢酸	◎	○	○	○	
イソ吉草酸	◎足のムレ	○			
ノネナール		◎			




# DEO - SMILE

デオ スマイル  
コットン消臭ストレッチテープ  
Quality Samples

Cotton	93%
Polyurethane	7%
ROLL 100m	
後染 Piece Dyeing	

**STRETCH**

## No.1910



- 瞬時に消臭。汗も尿もサッと消臭。  
汗や尿(アンモニア)などの液体の悪臭は瞬時に消臭します。
- 洗えば消臭力が回復。だから効果が長続き。  
何回洗濯しても効果が復元します。半永久的に消臭力を持続します。

洗濯時の注意事項  
1. 中性洗剤を使用して下さい。  
2. 漂白剤を使用の際は酸素系を使用して下さい。

- 染色も出来ます。  
染めるときにphを弱酸性にして下さい。

### ●染色堅牢度

試験項目	試験方法 /生地No	C/# 黒 (16mm)
洗濯(級)	JIS L 0844 A-2号	変 4-5
		汚 4-5
汗(級)	JIS L 0848 (酸・アルカリ)	変 5・5
		汚 4-5・4-5
摩擦(級)	JIS L 0849 II型	乾 4-5
		湿 2
水(級)	JIS L 0846	変 5
		汚 4-5
ドライクリーニング (級)	JIS L 0860 A-1号 (パークロロエチレン)	変 5
		汚 4-5

※洗濯収縮率<-6.7%

### ●試験結果 6mm C/# 半晒

[(社)繊維評価技術協議会にて]

臭気成分	初発濃度(ppm)	減少率 (基準値)	DEO-SMILE (半晒) [2時間後]	洗濯10回後
アンモニア	100	70%以上	99%以上 [10分後 76%]	98%
酢酸	50	80%以上	91%以上	95%
イソ吉草酸	約38	85%以上	97%以上	99%
ノネナール	約14	75%以上	93%以上	90%



## No.1920

消臭マイクロテープ  
Quality Samples


Nylon	87%
Polyurethane	13%
ROLL 100m	
後染 Piece Dyeing	

**STRETCH**

off




black



### 臭いを気にせず一日爽やか

消臭マイクロテープが気になる汗や加齢に伴う臭いを抑え、身につけたときから一日を終えるときまで着る人がずっと爽やかに、自信を持って快適に過ごせます。



消臭マイクロテープが嫌な臭いをきっちりカット。

### ●試験結果

アンモニアガスの除去性能評価試験(二時間後)

試料	初発濃度(ppm)	ガス濃度(ppm)	減少率(%)
原布	100	1.4	98
ブランク(空試験)	100	74	—

イソ吉草酸ガスの除去性能評価試験(二時間後)


試料	減少率(%)
原布	96

酢酸ガスの除去性能評価試験(二時間後)

試料	初発濃度(ppm)	ガス濃度(ppm)	減少率(%)
原布	50	2.1	91
ブランク(空試験)	50	24	—

ノネナールガスの除去性能評価試験(二時間後)

試料	減少率(%)
原布	97



FUNCTIONALITY



No.1911

# DEO HERRINGBONE

デオ ヘリンボン

Quality Samples

Polyester	100%
ROLL	30m
後染	Piece Dyeing



No.1912

# DEO SATIN

デオ サテン

Quality Samples

Polyester	100%
ROLL	30m
後染	Piece Dyeing



## 共通 Color Samples



No.1913

# DEO GROSGRAIN


デオ グログラン

Quality Samples

Polyester	100%
ROLL	30m
後染	Piece Dyeing



## Color Samples



FUNCTIONALITY



No.1914

# DEO KNIT

デオニット

Quality Samples

Polyester	100%
ROLL 30m	
後染 Piece Dyeing	



## Color Samples



No.1915


# DEO STRETCH

デオストレッチ

Quality Samples

	Size	5,8,12mm	7X7,9X9mm
Material			
Nylon	63%	70%	
Polyurethane	37%	30%	
ROLL 30m			
後染 Piece Dyeing			


**STRETCH**



## Color Samples



FUNCTIONALITY





# HIGH GRIP TAPE

ハイグリップテープ

## No.2106-PU

Quality Samples

10mm



13mm



Polyester	80%
Polyurethane	20%
ROLL 30m	
後染 Piece Dyeing	

**STRETCH**

## No.2107-PU

20mm



Polyester	70%
Polyurethane	30%
ROLL 30m	
後染 Piece Dyeing	

**STRETCH**

## No.2108-PU

薄手タイプ

30mm



Polyester	86%
Polyurethane	14%
ROLL 30m	
後染 Piece Dyeing	

**STRETCH**

# HIGH GRIP BINDER TAPE

ハイグリップバインダーテープ

## No.2109-PU

Quality Samples

7.5×7.5mm  
(15W)



## No.2110-PU

10×10mm  
(20W)



Polyester	88%
Polyurethane	12%
ROLL 30m	
後染 Piece Dyeing	

**STRETCH**

共通Color Samples

1  
(Off)



60  
(BK)





No.2105-PU

# HIGH GRIP TAPE


ハイグリップテープ

(超極細繊維が生み出すグリップ効果によるフィッティングの向上とソフトな肌触り)


Quality Samples

Material	Size	20mm	25mm	30mm	63mm	100mm
Polyester		85%	84%	83%	88%	81%
Polyurethane		15%	16%	17%	12%	19%
		ROLL 30m			ROLL 10m	
後染 Piece Dyeing						

**STRETCH**



共通Color Samples



FUNCTIONALITY



No.6027


# GRIP TAPE

グリップ テープ


Quality Samples

Polyurethane	71%
Nylon	29%
ROLL 30m	
後染 Piece Dyeing	

**STRETCH**



## Color Samples



## 皮膚障害を最低限までに抑えた、極薄滑り止めテープ

This is the ultra light-grip tape with making a least damage skin damage.

■摩擦抵抗の大きいシリコンに比べ、優しく滑り止め効果を発揮します。 This tape makes better anti-slip effect than the silicon with large frictional resistance.

■薄手タイプですので、生地裏側に付けても表側に付けても表面にひびきづらく、目立たずお使い頂けます。


Thanks to the tape with light type, you can use easily without making bad effect on the surface to the front even with the back of the texture.

## EXAMPLE

別注のホットメルトタイプは生地にスマートに圧着でき、縦裂に比べ、キレイに仕上がります。合わせてご検討下さい。

### 生地にひびきづらく、使いやすい薄手タイプの滑り止め

This tape makes no damage on the texture and is the light-ant-slip type for using easily.




## GRIP POWER

### 摩擦抵抗実試験

本商品の滑り止め効果を数値化することで、客観的に滑り止めの効力測定しています。社内試験による計測ですので参考程度にご覧下さい

#### 【試験方法】

- クラフトテープに試験試料を貼付け、巾15mm、長さ300mmにカットする。
- はね秤をつり下げる。ループ状の方に試験試料をつなぐ。
- 4kgの錘を試験試料の端にのせ、ばね秤を水平に一定の力でゆっくりと引っ張り、テープが1cm動いた時点で秤の表示を読み取る。



#### 【試験結果】

テープが1cm動くのに要した最大荷量

6027	シリコン ディスペンサー	ポリウレタン 織り込みテープ	滑り止め 加工なしテープ
2.9kg	2.8kg	2.3kg	0.4kg





# SHAPE-MEMORY TAPE

ネット テープ  
Quality Samples

〈形状保持〉

N1003

0



9



Polyester	25%
Nylon	49%
Polyethylene	26%
ROLL 100m	
先染 Yarn Dyeing	

N3003

0



9



Polyester	19%
Nylon	29%
Polyethylene	52%
ROLL 100m	
先染 Yarn Dyeing	

N8000

0



9



Polyester	17%
Nylon	28%
Polyethylene	55%
ROLL 100m	
先染 Yarn Dyeing	


# SHAPE-MEMORY TAPE

テクノス テープ  
Quality Samples

〈形状保持〉

T3000-1 10mm

0




9



Polyester	87%
Polyethylene	13%
ROLL 100m	
先染 Yarn Dyeing	

T3000-1 15mm

0




9



Polyester	92%
Polyethylene	8%
ROLL 100m	
先染 Yarn Dyeing	

T8000-1 10mm

0



9



Polyester	72%
Polyethylene	28%
ROLL 100m	
先染 Yarn Dyeing	

T8000-1 15mm

0



9



Polyester	79%
Polyethylene	21%
ROLL 100m	
先染 Yarn Dyeing	

T8000-2 15mm

0



Polyester	72%
Polyethylene	28%
ROLL 100m	
先染 Yarn Dyeing	



# REFLECTIVE ELASTIC CORD

反射 丸ゴム

## No.3112-TR

ハードタイプ

Polyester	70%
Rubber	30%
HANK 50m	
先染 Yarn Dyeing	

**STRETCH**

## No.3112-TSR

ソフトタイプ

Rubber	70%
Polyester	30%
HANK 50m	
先染 Yarn Dyeing	

**STRETCH**


Quality Samples



Quality Samples



共通 Color Samples



## No.3113-TR

8打ちタイプ


Quality Samples



Rubber	51%
Polyester	49%
HANK 50m	
先染 Yarn Dyeing	

**STRETCH**

Color Samples



FUNCTIONALITY





# REFLECTIVE CORD

反射コード

## Quality Samples

**No.4008**

ストレッチタイプ



Nylon	64%
Polyester	23%
Polyurethane	13%
ROLL 50m	
後染 Piece Dyeing	

**STRETCH**


## Quality Samples

**No.4007**



Nylon	79%
Polyester	21%
ROLL 50m	
後染 Piece Dyeing	

## Color Samples



## Color Samples

**No.4025**



Polyester	100%
HANK 50m	
先染 Yarn Dyeing	

## Color Samples

**No.4026**



Polyester	100%
HANK 50m	
先染 Yarn Dyeing	

## Color Samples

**No.4027**



Polyester	100%
HANK 50m	
先染 Yarn Dyeing	



FUNCTIONALITY

# REFLECTIVE TAPE

反射 テープ


No.4005

Polyester	100%
ROLL 30m	



No.4046

Polyester	100%
ROLL 30m	
先染 Yarn Dyeing	



No.4006

Polyester	100%
ROLL 30m	



# TRICOLOR REFLECTIVE TAPE

トリコロール 反射 テープ

No.4028

Polyester	100%
ROLL 50m	
先染 Yarn Dyeing	

Quality Samples



No.4029

Polyester	100%
ROLL 50m	
先染 Yarn Dyeing	

Quality Samples




# REFLECTIVE TAPE

反射 テープ

No.4010

Polyester	73%
Nylon	27%
ROLL 30m	
後染 Piece Dyeing	

Color Samples



No.4012

Nylon	72%
Polyester	28%
ROLL 30m	
後染 Piece Dyeing	


Color Samples



No.4011

Color Samples

Polyester	90%
Nylon	10%
ROLL 30m	
後染 Piece Dyeing	



FUNCTIONALITY





# REFLECTIVE TAPE

反射テープ

Quality Samples

Polyester	100%
ROLL 50m	
先染 Yarn Dyeing	

No.4019

9mm



No.4020

13mm




No.4021

18mm



## 共通Color Samples



No.4043

3M Scotchlite™

Quality Samples

10mm



No.4044

3M Scotchlite™

Quality Samples

15mm




Polyester	100%
ROLL 30m	
先染 Yarn Dyeing	

No.4001

## Color Samples

Nylon	86%
Polyester	14%
ROLL 30m	
後染 Piece Dyeing	





# REFLECTIVE PIPING

反射 パイピング  
Quality Samples

Polyester	100%
ROLL 100m	
先染 Yarn Dyeing	


No.25856



No.25857



## 共通 Color Samples



## Quality Samples

No.4009



Nylon	87%
Polyester	13%
ROLL 30m	
後染 Piece Dyeing	

No.4000



Nylon	91%
Polyester	9%
ROLL 30m	
後染 Piece Dyeing	

## 共通 Color Samples



No.4023


## Color Samples



Acrylic	45%
Rayon	17%
Polyester	38%
ROLL 30m	
先染 Yarn Dyeing	

No.4024

## Color Samples



S	Polyester	68%
	Rayon	32%
M	Polyester	78%
	Rayon	22%
ROLL 30m		
先染 Yarn Dyeing		

